

CM 920 Design



INDUSTRIAL **PUMPABLE** **EXPOSED SELF-LEVELING COMPOUND**

CM 920 Design is a pigmented, pumpable self-levelling compound.

Intended Use

The CM 920 Design is suitable for new construction and renovation. The product is intended for indoor use on concrete and other hard substrates. The product may be used as an wear surface in fx. domestic areas, offices spaces or shopping malls.

Pre-treatment

The substrate should be clean and free of dust, cement skin, grease and other impurities that can prevent adhesion. Adhesion and surface resistance of the substrate should be no less than 1.5 MPa. Always prime the underlying substrate with PP 600 and allow to dry before pouring. In terms of the primer forming a film and the curing of the self-leveling, the temperature of the substrate must not fall below 10 °C. For best results, the ambient temperature in the work area should be between 10 and 25 °C. At higher or lower temperatures, the time for curing will shorten or extend. With the risk for cracks due to shrinkage or settings in the subfloor, a concrete surface should not be leveled within the first 28 days after casting. As a recommendation the RH in the concrete should have reached RH 90 % as the upper limit for pouring the CM 920 Design. Use the Combimix form foam for edging. In order to avoid drainage pipes from getting clogged, always make sure the drains are properly sealed before pouring.

Mixing


Mix the dry powder with 3.8–4.0 liters of water (19–20 %) per 20 kg bag. Mix with a drilling machine and a whisk, or a mixing pump intended for this purpose. Best results are achieved when mixing in a barrel. The correct water mixture can be tested using a slump test with a cylinder with Ø 30 mm and a height of 50 mm on a 300 x 300 mm plexiglas plate. With the correct water mixture, the spread should be max 140 mm. The slump test also checks that the material is well blended and that there is no separation.

Water requirement



3.8–4.0 l/20 kg

Mixing time



2+1 min

Workable



15–20 min

Working temperature



10–25 °C

Walkable



approx. 2 hrs

Weather protection



CM 920 Design



INDUSTRIAL

PUMPABLE

EXPOSED SELF-LEVELING COMPOUND

CM 920 Design is a pigmented, pumpable self-levelling compound.

Execution

The mixed material is applied by hand, or pumped out onto the substrate in lengths. Each new ribbon is added to the old one as soon as possible so that the material can blend together and create an even surface. The width of the ribbons can be adjusted to the capacity of the mixing pump and the thickness of the covering. The material requires a light treatment with a trowel to provide maximum smoothness.

Post-treatment and curing

You can easily shape or cut the semi-hardened self-leveling underlayment material before it fully dries. The product is paintable with epoxy or similar after 2–5 days depending on the thickness. Always make sure that the material is sufficiently dry before it gets overcoated. The guiding value assumes a curing temperature of approximately 20 °C, 50 % RH and proper air flow.

Storage time and packaging

Store in a dry environment, on an unopened plastic-coated pallet, six months from the date of production. The date of production is printed on the packaging. CM 920 Design is delivered in 20 kg bags.

Residual Products and Safety Instructions

Plasticbag: Recycle empty and cleaned sacks. Paperbag: Empty packaging is sorted as residual waste. Any remaining, dry powder that has been stored properly can be used again. Hardened material should be disposed of as construction waste. Do not wash the product into the sewage system. Follow regulations in each respective country.

HMS Info

For current version of product information, contact Combimix at info@combimix.se. Previously undated and dated issues are no longer valid. For more information contact our sales organization.

CM 920 Design



INDUSTRIAL

PUMPABLE

EXPOSED SELF-LEVELING COMPOUND

CM 920 Design is a pigmented, pumpable self-levelling compound.

Disclaimer

pdf-disclaimer

CM 920 Design



INDUSTRIAL

PUMPABLE

EXPOSED SELF-LEVELING COMPOUND

CM 920 Design is a pigmented, pumpable self-levelling compound.

Product specification

Environment	indoor
Substrate	concrete, ceramic tiles/clinker, stone, heated floor systems
Slope construction	no
Leveling layer	5–15 mm
Grain size	≤ 1 mm
Material consumption	1,7 kg/m ² /mm
Water requirement	3.8–4.0 l/20 kg
Flowability	140 mm
Working temperature	10–25 °C
Mixing time	2+1 min
Workable	15–20 min
Drying time category	sjalvtorkande
Walkable	approx. 2 hrs
paintableEpoxy	2–5 days
Water damage resistant	yes
Free shrinkage	≤ 0,03 %
Final surface	clinker, limmade-plastmattor, loslagt-tragolv, tatskikt, epoxy-pu, finished floor surface, limmad-parkett
Release of corrosive substances	CT (as per EN 13813)
Compressive strength class	C30 (as per EN 13813)
Compressive strength, average	32 MPa (as per EN 13813)
Flexural strength class	F6 (as per EN 13813)
Flexural strength class, average	7,5 MPa (as per EN 13813)
Fire class / Reaction to fire	A1fl (as per EN 13813)

CM 920 Design



INDUSTRIAL PUMPABLE EXPOSED SELF-LEVELING COMPOUND

CM 920 Design is a pigmented, pumpable self-levelling compound.

RWA	100 (as per EN 13813)
Adhesion	B1.5 (as per EN 13813)